

INDUSTRIAL PRODUCTS

Source: Lima, OH

Alternate Names:

page 1 of 1

CHEMICAL ANALYSIS	TYPICAL	GUARANTEE
Assay, Wt. %		99.4 min.
Total Nitrogen, as N, Wt. %		46.4 min.
Moisture, as H ₂ O, Wt. %		0.3 max.
Alkalinity, as Ammonia, ppm		100 max.
Biuret, Wt. %		0.3 max.
Iron, as Fe, ppm		1 max.
Ash, ppm		10.0 max.
pH, 10% Solution @ 68°F		7.5 - 9.5
Formaldehyde, ppm		3 max.

PHYSICAL DATA	TYPICAL	GUARANTEE
Color, APHA	10 max.	
Turbidity, as SiO ₂ , ppm	20 max.	
Bulk Density, lbs/ft ³	45 - 48	
Size Range, Tyler Mesh, Wt. %, -5m	100	
+20m	99	
Size Guide Number (SGN) (as made):		
- Average	200	
- Range	180 - 220	
Angle of Repose, degrees	28°	